

Display Film BO 250 WB

250 µm

Material Description High quality block out film with a polypropylene and polyester base. This multi layer film is tear resistant, has no transmit of light and has a proper stiffness. Perfect for high quality reproductions and a diversity of applications.

- Qualifications**
- A fine Matt coated finish
 - PET & PP base material
 - Print side: matt white surface
 - Reverse side: White satin
 - Available in 36+, 42-~~x~~ 30m
 - Core size: 2+

- Details**
- Suitable printing condition: temperature 15-30°C / humidity 30-60%
 - Dye based inks and pigmented inks are compatible
 - Over laminating, the printer material prolong the life of the print
 - Ambient temperature and weather can affect the condition of the product




- Applications**
- Presentation systems (roll ups, etc...)
 - Shop display
 - Presentations
 - Exhibitions

Physical Properties

Quality		PET & PP
Weight		215g/m ²
Thickness		250 µm test method: ASTM D645
Print side		Matt Instant dry coating
Reverse side		White satin
L.a.b.		85/1/-7 test method: ANSI T (D50/2°/Abs/No)
yellowness		30 test method: ASTM D1925
glossiness		3/5 test method: ASTM 2457

Compatibility

Hewlett packard
Epson
Canon
Oce
And more...

-  WB Pigment (UV)
-  WB Dye
-  Latex

Make your own practical test to be sure it reaches your quality standard.
 For all- and latest information see our Compatibility List.

Printing guidelines

Ink restrictions and heater settings have to be set for specific printer ink combinations to obtain the best results.

Colour profiles

ATgraphix develops high quality ICC colour profiles for the divers printing media's. We work with specialists who can produce your profile if it's not direct available from our library. Please contact us for the possibilities.

Storage conditions

1 year under normal conditions (10. 25°C at a relative humidity of 50 %). Higher humidity and/or temperature can affect the product performance. Always store the media in a dark place.

Environment

The media and final prints can be disposed of as polyester Material is suitable for recycling.
 Please consult local recycle resources.